Progress in Photocatalysis of g-C₃N₄ and its Modified Compounds

Yanling Wu^{1,*}, Yanmin Wang¹ and Miantuo Li¹

¹School of transportation and civil engineering, Shandong Jiaotong University, Jinan, China

Abstract. Recently, graphitic carbon nitride (g-C₃N₄), a polymeric semiconductor has been widely used as a low-cost, stable, and metal-free visible-light-active photocatalyst in the sustainable utilization of solar energy, such as water splitting, organic photosynthesis, and environmental remediation, which has attracted world wide attention from energy and environmental relative fields. Base on analysis of structure and theoretical calculation, the reasons that g-C₃N₄ can be used as a non-metallic catalyst were discussed in this paper. Some group's research jobs that metal-supported g-C₃N₄, metal-supported g-C₃N₄/organic semiconductor compound and heterogeneous junction adjust the semiconductor electronic band structure have been summarized. And the mechanism, effect factors, and research developments on the reaction of organic degradation by photocatalytic and splitting water for hydrogen revolution catalyzed by above-mentioned modified g-C₃N₄ were emphatically analyzed. Finally, the prospects for the development of highly efficient g-C₃N₄ based photocatalysts are also discussed.

1 Introduction

Along with the rapid development of modern industrialization in recent years, people's demand for energy is increasing day by day, consuming a large amount of non-renewable fossil fuels (such as coal, oil, and natural gas) and discharging greenhouse gases (such as CO₂, SO₂, and NO_x) and toxic gases cause serious energy crisis and environmental degradation, which make human beings face severe survival challenges[1]. Solar energy is an inexhaustible one-time energy, which is one of the most interesting research topics. Finding suitable semiconductors as photocatalysts capable of converting solar energy is an important task in materials science. Most photocatalysts currently face the same problem[2]: (1) It can only respond to less than 5% of the solar radiation in ultraviolet light due to the wide band gap, and it has a low visible-light utilization of 47% of solar energy; (2) The potential of valence and conduction bands is difficult to meet the potential needs of various catalytic reactions at the same time; (3) Photogenerated electron-hole recombination is easy, quantum efficiency is very low. The light elements of group III and group V combine through 2p and 3p orbitals, which cause unique and diverse physicochemical properties due to their short atomic spacing. Carbon and nitrogen elements have only two atomic shells with small radius, which can form strong covalent bonds with each other, and can also form isotropic dense three-dimensional covalent mesh structure through quadruple coordination. Berzelius and Liebig synthesized a polymerized carbon nitride named it as a melon and carried out relevant reports for the first

time, which is the earliest known report on synthetic polymers. Since Liu and Cohen[3] put forward β -C₃N₄ covalent crystal theoretically, carbon and nitrogen compounds have attracted the attention of scientists all over the world due to their excellent properties in optics and mechanics. Teter and Hemley[4] of Carnegie Institute, Washington, used conjugate gradient method to recalculate C₃N₄, and concluded that C₃N₄ may have five structures (namely, alpha phase, beta phase, cubic phase, quasi-cubic phase, and graphite-like phase, respectively.). Among them, graphite-like phase of g-C₃N₄ with non-toxic and visible light response (semiconductor band gap: 2.7 eV) and other properties is the most stable phase at room temperature, which makes it have a promising in the field of catalysis. The g-C₃N₄ has attracted great attention in photocatalytic applications[5-8] (such as hydrogen production, organic synthesis and pollutant degradation) because of its outstanding advantages of high photocatalytic activity, good stability and low price of raw materials, especially metal-free materials. In this paper, the reaction principle, the main problems, research status and development trend of g-C₃N₄ semiconductor photocatalysis are summarized.

2 Photocatalytic mechanism analysis of g-C₃N₄

g-C₃N₄ is a typical polymer semiconductor, in which the C and N atoms are hybridized with sp² to form highly delocalized π conjugated system[9-11]. The g-C₃N₄ is an electron-rich organic semiconductor, and the band gap between them is ~ 2.7 eV, which can absorb

* Corresponding author: wuyanling621@163.com

blue and purple light with wavelength less than 475 nm in the solar spectrum[9,12,13]. Among them, Npz orbitals form the highest occupied molecular orbital (HOMO) of g-C₃N₄, Cpz orbitals form the lowest unoccupied molecular orbital (LUMO) of g-C₃N₄. Analysis result shows that nitrogen atoms can be used as the preferred oxidation site for H₂O decomposition to produce O₂, while carbon atoms provide the reduction site for H⁺ to H₂. The electrons from the VB are excited to the CB, leaving holes in the VB when the light energy is greater than or equal to the gap of semiconductor photocatalyst. The electrons and holes produced by light can cause reduction and oxidation reactions, respectively. To satisfy the energy of water splitting, the bottom of the CB is negative to the reduction potential of water (0 V vs NHE at pH = 0), while the top of the VB must be positive to the oxidation potential of water (1.23 V vs NHE). Therefore, A minimum photoelectron energy required for a thermodynamic reaction must be up to 1.23 eV. The absolute values of the oxidation and reduction energy levels of H₂O molecules calculated by the calculation method are located between the energy gap of g-C₃N₄[10]. In addition, compared with traditional TiO₂ photocatalyst, g-C₃N₄ can also effectively activate molecular oxygen to produce superoxide radicals for photocatalytic conversion of organic functional groups and photocatalytic degradation of organic pollutants[14] or inhibit the formation of hydroxyl radicals with strong oxidation ability to avoid peroxidation of organic functional groups[15]. It can be used as visible photocatalyst for photocatalytic conversion of solar energy in theory.

3 Preparation, properties and photocatalytic study of metal-supported g-C₃N₄

g-C₃N₄ with an energy gap of 2.7 eV, can be used as a non-metallic photocatalyst for hydrogen evolution and oxygen release under ultraviolet and visible light. The g-C₃N₄ catalyst can show catalytic activity for reducing water hydrogen evolution reaction or oxygen release reaction without metal cocatalyst when suitable sacrificial electron acceptor or donor exists, respectively. However, the hydrogen evolution activity of pure g-C₃N₄ fluctuates greatly, the yield of different reactors is different (0.1-4.0 μ mol/h), which can be solved by modification with a small amount of metal (such as Pt etc.)[16]. The deposition of metals on the surface of g-C₃N₄ can effectively capture photogenerated electrons in the CB, and can be used as the active sites of the reaction, thus increasing the catalytic yield. In addition, the structure of g-C₃N₄ is filled with six unshared electron pairs of nitrogen atoms, making it an ideal place to house metal atoms. Therefore, metal loading is a feasible method to improve catalytic efficiency. Besides, metal loading can improve other properties of g-C₃N₄ (such as permeability)[17].

Wang' research group [18] first used monocyanoamide to prepare g-C₃N₄ to decompose water under visible light (wavelength greater than 420 nm) to produce H₂. The

rate at which unmodified g-C₃N₄ releases H₂ varies from 0.1 mol/L to 4.0 mol/L, and the ability to release H₂ can be significantly changed by a small amount of doping Pt. The amount of H₂ released by Pt-g-C₃N₄ with a mass fraction of 3.0% Pt is 10.7 mol/h, and 770 mol/h is released within 72 h. In the same year, Maeda et al. of the University of Tokyo[19] synthesized g-C₃N₄ deposited by Pt, Pb, Rh, Ru and other noble metals by the method of photodeposition to conduct the experiment of reducing H₂O to H₂. 0.1 g of g-C₃N₄ catalyst powder deposited with noble metal was put into 100 mL water, in which triethanol amine containing 10% volume fraction was used as sacrifice agent. Under visible light irradiation with a wavelength greater than 420 nm, Pt-g-C₃N₄ with a mass fraction of Pt released H₂ at a rate of 7.3 mol/h, and Pd-g-C₃N₄ with a mass fraction of Pd released H₂ at a rate of 5.3 mol/h. The yield of hydrogen evolution was increased by about 7 times when the surface of g-C₃N₄ was loaded with Pt nanoparticles.

The results show that compared with the covalent bond fracture from the hydrogen-rich surface of g-C₃N₄, the hydrogen elimination from the surface of g-C₃N₄ containing the Pt-H bond is easier. Di et al.[20] reported a principle that the Fermi level can be automatically adjusted to obtain negative voltage based on the special quantization charging properties of Au nanoparticles, and Au nanoparticles are deposited in the surface of g-C₃N₄ semiconductor materials by deposition precipitation, optical deposition, injection and so on. The results show that Au/g-C₃N₄ prepared by deposition precipitation method has high catalytic activity due to the formation of tight metal-semiconductor heterojunction. The surface of the g-C₃N₄ loaded Au nanoparticles capture and store the electrons generated by the illumination matrix, which change the Fermi level and make it more negative. The process improves the transmission ability of electrons from the CB in the g-C₃N₄ to the Au.

Researchers have found that cocatalytic coupling agents can be used as efficient photocatalysts in water splitting reactions. Pradhan et al.[21] synthesized g-C₃N₄ hybridization (denoted as PtAu/g-C₃N₄) of bimetallic PtAu alloy nanoparticles by a simple solvent-thermal method. PtAu/g-C₃N₄ hybrids have high light absorption ability, which leads to the formation of more carriers and better electron transport properties, thus making them have better photocatalytic activity. The contents of Pt and Au in bimetallic alloys were changed by changing the initial Pt and the concentration of Au precursors. Under the visible light irradiation with a wavelength of more than 420 nm, the H₂ generation rate is 1009 μ mol/g/h, which is ten times of the hydrogen generation rate of g-C₃N₄, but also far more than Pt/g-C₃N₄ (281 μ mol/g/h) and Au/g-C₃N₄ (253 μ mol/g/h). The hydrogen production rate of PtAu/g-C₃N₄ hybrid is 713 μ mol/g/h after 5 h test, which still has high photocatalytic activity, thus achieving better stability.

4 Study on the sensitization of g-C₃N₄ photocatalyst

g-C₃N₄ photocatalyst can only absorb blue and purple light with energy greater than 2.7 eV in theory due to the π conjugated structural characteristics of the heptazine ring[12,13]. Therefore, how to expand the absorption wavelength of g-C₃N₄ has become an important problem in photocatalytic research. So far, in addition to copolymerization modification and semiconductor doping, surface sensitization, such as dye sensitization and semiconductor sensitization, has also been developed to modify g-C₃N₄ to improve its visible light utilization. However, the three highest occupied molecular orbitals (HOMOs) in g-C₃N₄ itself have p symmetry characteristics, in which HOMO-3 is formed by the reverse combination of pz orbital of pyridine nitrogen. It conforms to the symmetry of the highest unoccupied p orbit in the Huxler benzene ring model. The electron structure can cause charge transfer, that is, charge transfer from g-C₃N₄ to benzene ring, which causes "organic" activation of aromatic ring and provides necessary conditions for catalyzing a series of reactions of aromatic ring. If the lamellae of g-C₃N₄ is infinitely large, and the activation will affect the defects with higher electron localization ability and the edge of the lamellae.

Zang' Group[22] prepared perylene tetracarboxylic diimides (PTCDIs)/Pt/g-C₃N₄ photocatalyst that the loading of PTCDIs on the surface of Pt/g-C₃N₄. Compared with Pt/g-C₃N₄, PTCDIs/Pt/g-C₃N₄ extends the range of visible light and produces hydrogen around ~0.375 mol/h in the presence of triethanolamine as a sacrifice agent, which is ten times higher than Pt/g-C₃N₄ at $\lambda > 420$ nm. Zeng' group[23] using fluorescein as photosensitizer has greatly improved the Ag/g-C₃N₄ hydrogen production rate. And the synergies between the each composition best Ag load to endow them with excellent photocatalytic performance in the case of triethanolamine as sacrifice agent. Under the irradiation of sunlight to produce hydrogen rate of 2014.20 $\mu\text{mol/g/h}$, which is 4.8 times of not sensitized Ag/g-C₃N₄. Fan' group[24] used EY sensitization Au/g-C₃N₄, and confirmed that photogenerated electrons transferred from EY to the conduction band of g-C₃N₄ would eventually be transferred to Au co-catalyst, thus inhibiting carrier recombination and effectively improving the photocatalytic hydrogen production activity. The hydrogen production rate is 660.8 mol/h·g under visible light $\lambda > 400$ nm, which is 3.5 times of the hydrogen production rate of Au/g-C₃N₄. Wu' group[25] used fluorescein-sensitized Cu₂(OH)₂CO₃/g-C₃N₄ nanocomposite photocatalytic system, and the hydrogen production rate is 22.6 mol/h under visible light > 400 nm, which is 19.3 and 3.8 times that of pure g-C₃N₄ and unsensitized Cu₂(OH)₂CO₃/g-C₃N₄, respectively.

5 Application of g-C₃N₄-based heterojunction photocatalyst

In the modification method of g-C₃N₄, by constructing heterostructure with another type of semiconductor material, the advantages of multicomponent can be combined. The interface formed can reduce the recombination of photoinduced charge and improve the absorptivity of visible light. Meanwhile, the high redox ability of electrons and holes is maintained[26]. Therefore, design and synthesis of different types of g-C₃N₄-base heterojunction photocatalyst has important research value for achieving efficient photodegradation of pollutants and improving the increasingly serious environmental pollution[27]. In recent years, photocatalysts for type II-heterojunctions[28], g-C₃N₄-based p-n heterojunctions[29] and Z-scheme heterojunctions[30] have been developed rapidly and have shown great potential advantages in various photocatalytic systems. By constructing different types of heterostructures, the photocatalytic performance of g-C₃N₄ has been greatly improved.

At the interface between the two semiconductors, band bending will occur at the type II-heterojunction, forming a built-in electric field, and the photogenerated electrons and holes will migrate in reverse, thus reducing the recombination of photogenerated electrons and holes[31,32]. Li et al.[33] synthesized the hierarchical porous ZnO/g-C₃N₄ composites with II-heterostructures by two-step method. The ZnO/g-C₃N₄ can effectively degrade rhodamine B by improving the efficiency of charge separation. After exposure to UV lamp for 30 min, g-C₃N₄ can photodegrade 93.8% of rhodamine, while ZnO/g-C₃N₄ can degrade 100% of rhodamine B, showing excellent photocatalytic activity, and after five cycle tests, the degradation rate was still up to 95.2%. Moreover, X-ray diffraction spectrum showed that after cycling test, the structure of ZnO/g-C₃N₄ has not changed, showing good durability. The separation efficiency of electron-hole pairs in p-n heterojunctions is faster than that of II-heterojunctions, and the photocatalytic activity is greatly improved compared with II-heterojunctions[34]. Cai et al.[35] prepared a new p-n heterojunction of g-C₃N₄/CuS photocatalyst by in situ synthesis technology. The degradation rate of g-C₃N₄/CuS heterogeneous for rhodamine B and methylene blue is 8.914 and 13.543 times for pure g-C₃N₄, and is 3.032 and 6.373 times for CuS, respectively. The enhancement of photocatalytic performance is attributed to the interaction between g-C₃N₄ and CuS as well as the matching overlapping band structure. Under the irradiation of visible light, the charge carriers of CuS and g-C₃N₄ can be excited simultaneously. The energy of the valence band of g-C₃N₄ is lower than that of CuS, so the photogenerated holes in the valence band of CuS can easily migrate to the valence band of g-C₃N₄. Meanwhile, due to the conduction band energy of g-C₃N₄ is greater than that of the CuS, the photogenerated electrons of g-C₃N₄ on conduction band can be quickly transferred to the CuS conduction band, thus reducing the photogenerated

electrons and hole recombination. Liu et al.[36] constructed a new type of Z-scheme heterojunction photocatalyst (CDs/g-C₃N₄/MoO₃) modified by carbon quantum dots. MoO₃, as a typical p-type metal oxide semiconductor, is regarded as the best choice for constructing Z-scheme heterojunction photocatalyst due to its unique energy and electrochemical characteristics[37]. Carbon quantum dots (CDs) have excellent upconversion photoluminescence properties, as well as excellent photoluminescence transfer and reservoir properties, which contribute to the efficient use of visible light by catalysts[38]. After 90 min of visible light irradiation, MoO₃ and pure g-C₃N₄ only degrade 10.1% and 5.3% of tetracycline, while CDs/g-C₃N₄/MoO₃ can degrade 88.4% of tetracycline. And after the three cycle operation, the degradation amount of tetracycline remained at 81.0%, and the structure of the catalyst did not change significantly after the photocatalytic reaction, which achieved excellent structural stability.

6 Summary and outlook

Addressing traditional photocatalyst of g-C₃N₄ has the problems of small specific surface area, high exciton binding energy, serious photogenerated carrier recombination and large band gap, which can not make effective use of solar light. A large number of research work has been carried out on composition-structure-performance regulation of g-C₃N₄, and many important research results have been obtained, which has deepened an understanding of the nature and basic law of g-C₃N₄ photocatalytic action. The next step study of photocatalysis laid a solid foundation[39].

In the future, the photocatalytic study of g-C₃N₄ can be carried out from the following aspects. (1) g-C₃N₄ photocatalyst was jointly modified by multiple methods. For example, combining copolymerization with nanostructure regulation can optimize the chemical composition of materials and regulate their semiconductor band structure, on the other hand, it can control the nanostructure and surface morphology of materials, so as to improve the kinetic process in multiple photocatalytic reactions. (2) The application of g-C₃N₄ in photocatalysis was further expanded, especially in organic selective photosynthesis and CO₂ photocatalytic reduction. g-C₃N₄ is suitable for selective conversion of organic functional groups and reduction fixation of CO₂ due to its unique band structure and material properties of organic semiconductors. (3) Theoretical calculations and experimental studies show that g-C₃N₄ with suitable conduction and valence bands, which can be used as photocatalysts for fully hydrolyzed water. Hence, screening and designing suitable hydrogen and oxygen-producing cocatalysts for g-C₃N₄ is expected to be realize photocatalytic total hydrolysis of water by surface modification and optimization of chemical reaction kinetics.

Acknowledgments

This work is financially supported by the Doctoral Scientific Research Foundation of Shandong Jiaotong University (BS50004952) and the Scientific Research Fund Project of Shandong Jiaotong University (Z201918).

References

1. Zhang J.N., Hu W.P., Cao S., Piao L.Y. Recent progress for hydrogen production by photocatalytic natural or simulated seawater splitting[J]. *Nano Research*, 2020, 13: 2313-2322.
2. Han B., and Hu Y.H. Highly Efficient Temperature-Induced Visible Light Photocatalytic Hydrogen Production from Water[J]. *J. Phys. Chem. C*, 2015, 119: 18927-18934.
3. Liu A.Y., Cohen M.L. Prediction of new low compressibility solids[J]. *Science*, 1989, 245(4920): 841-842.
4. Teter D.M., Hemley R.J. Low-compressibility carbon ni-tride[J]. *Science*, 1996, 271: 53-55.
5. Da Silva E.S., Moura N.M.M., Coutinho A., et al. β -Cyclodextrin as a precursor to holey C-doped g-C₃N₄ nanosheets for photocatalytic hydrogen generation[J]. *ChemSusChem*, 2018, 11: 2681-2694.
6. Lima M.J., Silva A.M.T., Silva C.G., et al. Graphitic carbon nitride modified by thermal, chemical and mechanical processes as metal-free photocatalyst for the selective synthesis of benzaldehyde from benzyl alcohol[J]. *J. Catal*, 2017, 353: 44-53.
7. Naseri A., Samadi M., Pourjavadi A.Z., et al. Graphitic carbon nitride (g-C₃N₄)-based photocatalysts for solar hydrogen generation: recent advances and future development directions[J]. *J. Mater. Chem. A*, 2017, A 5: 23406-23433.
8. Giannakoudakis D.A., Hu Y., Florent M., et al. Smart textiles of MOF/g-C₃N₄ nanospheres for the rapid detection/detoxification of chemical warfare agents[J]. *Nanoscale Horizons*, 2017, 2: 356-364.
9. Wang X.C., Maeda K., Thomas A., et al. A metal-free polymeric photocatalyst for hydrogen production from water under visible light[J]. *Nat. Mater.*, 2009, 8: 76-80.
10. Zhang J.S., Chen X.F., Takane K., et al. Synthesis of a carbon nitride structure for visible-light catalysis by copolymerization[J]. *Angew. Chem. Int. Ed.*, 2010, 49(2): 441-444.
11. Cui Y.J., Ding Z.X., Liu P., et al. Metal-free activation of H₂O₂ by g-C₃N₄ under visible light irradiation for the degradation of organic pollutants[J]. *Phys. Chem. Chem. Phys.*, 2012, 14: 1455-1462.
12. Liu J.H., Zhang T., Wang Z.G., et al. Simple pyrolysis of urea into graphitic carbon nitride with recyclable adsorption and photocatalytic activity[J]. *J. Mater. Chem.*, 2011, 21:14398-14401.

13. Maeda K., Wang X.C., Nishihara Y., et al. Photocatalytic activities of graphitic carbon nitride powder for water reduction and oxidation under visible light[J]. *J. Phys. Chem. C*, 2009, 113(12): 4940-4947.
14. Reuter K., Scheffler M. Composition, structure, and stability of RuO₂ (110) as a function of oxygen pressure[J]. *Physical Review B*, 2001, 65(3): 35406-49901.
15. Wang X.C., Blechert S., Antonietti M. Polymeric graphitic carbon nitride for heterogeneous photocatalysis[J]. *ACS Catal.*, 2012, 2(8):1596-1606.
16. Cheng N.Y., Tian J.Q., Liu Q., et al. Au-nanoparticle-loaded graphitic carbon nitride nanosheets: Green photocatalytic synthesis and application toward the degradation of organic pollutants[J]. *ACS Appl. Mater. Interfaces*, 2013, 5(15): 6815-6819.
17. Wang X.C., Mi W.B., Jiang E.Y., et al. Large magnetoresistance observed in facing-target sputtered Ni-doped CN_x amorphous composite films[J]. *Acta Materialia*, 2007, 55(10) : 3547-3553.
18. Ong W.J., Tan L.L., Ng Y.H., et al. Graphitic carbon nitride(g-C₃N₄)-based photocatalysts for artificial photosynthesis and environmental remediation: Are we a step closer to achieving sustainability?[J]. *Chem. Rev*, 2016, 116: 7159-7329.
19. Xu J., Wang G.X., Fan J.J., et al. g-C₃N₄ modified TiO₂ nanosheets with enhanced photoelectric conversion efficiency in dye-sensitized solar cells[J]. *Journal of Power Sources*, 2015, 274: 77-84.
20. Di Y., Wang X.C., Thomas A., et al. Making metal-carbon nitride heterojunctions for improved photocatalytic hydrogen evolution with visible light[J]. *ChemCatChem*, 2010, 2(7) : 834-838.
21. Bhunia K., Chandra M., Khilari S., et al. Bimetallic PtAu alloy nanoparticles-intergrated g-C₃N₄ as an efficient photocatalyst for water-to-hydrogen conversion[J]. *ACS Applied Materials & Interfaces*, 2018
22. Chen S., Wang C., Bunes B.R., et al. Enhancement of visible-light-driven photocatalytic H₂ evolution from water over g-C₃N₄ through combination with perylene diimide aggregates[J]. *Applied Catalysis A: General*, 2015, 498: 63-68.
23. Qin J., Huo J., Zhang P., Zeng J., et al. Improving the photocatalytic hydrogen production of Ag/g-C₃N₄ nanocomposites by dye-sensitization under visible irradiation[J]. *Nanoscale*, 2016, 8(4): 2249-2259.
24. Dang H., Tan G., Yang W., et al. Enhanced visible-light photocatalytic H₂ production of graphitic carbon nitride nanosheets by dye-sensitization combined with surface plasmon resonance[J]. *Journal of the Taiwan Institute of Chemical Engineers*, 2017, 78: 185-194.
25. Liu Y., Wu X., Lv H., et al. Boosting the photocatalytic hydrogen evolution activity of g-C₃N₄ nanosheets by Cu₂(OH)₂CO₃ modification and dye-sensitization[J]. *Dalton Trans.*, 2019, 48: 1217-1225.
26. Wang C., Fu M., Cao J., et al. BaWO₄/g-C₃N₄ heterostructure with excellent bifunctional photocatalytic performance[J]. *Chemical Engineering Journal*, 2020, 385: 123833.
27. Paul T., Das D., Das B.K., et al. CsPbBrCl₂/g-C₃N₄ type II heterojunction as efficient visible range photocatalyst[J]. *Journal of Hazardous Materials*, 2019, 380: 120855.
28. Wang C.H., Qin D.D., Shan D.L., et al. Assembly of g-C₃N₄-based type II and Z-scheme heterojunction anodes with improved charge separation for photoelectrochemical water oxidation[J]. *Phys Chem Phys*, 2017, 19: 4507-4515.
29. Yang L.Y., Liu J., Yang L.P., et al. Co₃O₄ imbedded g-C₃N₄ heterojunction photocatalysts for visible-light-driven hydrogen evolution[J]. *Renewable Energy*, 2020, 145: 691-698.
30. Xie Z.J., Feng Y.P., Wang F.L., et al. Synthesis of direct Z-scheme g-C₃N₄/Ag₂VO₂PO₄ photocatalysts with enhanced visible light photocatalytic activity[J]. *Separation and Purification Technology*, 2018, 195: 332-338.
31. Wang Y., Wang Q., Zhan X., et al. Visible light driven type II heterostructures and their enhanced photocatalysis properties: a review[J]. *Nanoscale*, 2013, 5, 8326-8339.
32. Marschall R. Photocatalysis: Semiconductor composites: Strategies for enhancing charge carrier separation to improve photocatalytic activity[J]. *Adv. Funct. Mater.* 2014 , 24: 2421-2440.
33. Wu S.J., Zhao H.J., Li C.F., et al, Type II heterojunction in hierarchically porous zinc oxide/graphitic carbon nitride microspheres promoting photocatalytic activity[J]. *Journal of Colloid and Interface Science*, 2018, 538: 99-107.
34. Ren Y.J., Zeng D.Q., Ong W.J. Interfacial engineering of graphitic carbon nitride (g-C₃N₄)-based metal sulfide heterojunction photocatalysts for energy conversion: a review[J]. *Chinese Journal of Catalysis*, 2019, 40: 289-319.
35. Cai Z., Zhou Y., Ma S., et al. Enhanced visible light photocatalytic performance of g-C₃N₄/CuS p-n heterojunctions for degradation of organic dyes[J]. *J. Photochem. Photobiol. A Chem.* 2017, 348: 168–178.
36. Xie Z.J., Feng Y.P., Wang F.L., et al. Construction of carbon dots modified MoO₃/g-C₃N₄ Z-scheme photocatalyst with enhanced visible-light photocatalytic activity for the degradation of tetracycline[J]. *Applied Catalysis B: Environmental*, 2018, 229: 96-104.
37. Huang L.Y., Xu, H., Zhang R.X., et al. Synthesis and characterization of g-C₃N₄/MoO₃ photocatalyst

- with improved visible-light photoactivity[J]. *Applied Surface Science*, 2013, 283: 25-32.
38. Li H.T., Liu R.H., Lian S.Y., et al. Near-infrared light controlled photocatalytic activity of carbon quantum dots for highly selective oxidation reaction[J]. *Nanoscale*, 2013, 5: 3289-3297.
39. Wang Y., Wang X.C., Antonietti M. Polymeric graphitic carbon nitride as a heterogeneous organocatalyst: From photochemistry to multipurpose catalysis to sustainable chemistry[J]. *Angew. Chem. Int. Ed.*, 2012, 51: 68-89.