Effect of various parameters on the workability and strength properties of geopolymer concrete

Nutakki Sai Ketana^{1*}, Srinivasa Reddy V², M V Seshagiri Rao³, and S Shrihari⁴

¹M. Tech (Structural Engineering), Department of Civil Engineering, GRIET, Hyderabad, India.

²Professor of Civil Engineering, GRIET, Hyderabad, India.

³Professor of Civil Engineering, CVR College of Engineering, Hyderabad, Telangana

⁴Professor of Civil Engineering, VJIT, Hyderabad, India.

Abstract. In the present study, effect of various molarities of NaOH, various fly ash content and alkaline activator solution (AAS) / fly ash(FA) ratios on the workability of geopolymer concrete(GPC) are studied along with the effect of use of Na₂SiO₃/NaOH and K₂SiO₃/KOH as alkaline activator solutions and various fly ash contents on the compressive strength of geopolymer concrete mixes. Observations shows that both Na₂SiO₃/NaOH and K₂SiO₃/KOH gives better performance for different molar, AAS/FA and oxide ratios. Class C GPC has better performance than Class F GPC. It was found that the increase in molarity decreases workability of geopolymer concrete. Also, the workability increases with increase in fly ash (FA) content and AAS/FA ratio in geopolymer concrete. Compressive and split tensile strengths decrease with increase in fly ash content.

1 Introduction

In India, coal with an ash level of about 40% is mostly utilised for thermal power generation. As a result, massive amounts of fly ash (FA) are produced in thermal power plants, generating a slew of disposal issues. FA disposal is becoming increasingly problematic, as only 15% of FA is now used for high-value-added uses such as concrete and building blocks, with the balance being used for land filling. Only around a quarter of the total yearly FA generated in the globe is actually used. For almost 60 years, fly ash has been utilised as a mineral additive component in Portland pozzolan mixed cement. The byproduct of blast furnaces used to produce iron is ground granulated blast furnace slag (GGBS). ²GGBS is a non-metallic, glassy, granular substance made mostly of calcium and various base silicates and aluminates. Slag with a specific surface area of 400 to 600 m²/kg will be processed to less than 45 micron from a coarser, popcorn-like friable structure (Blaine). The particle size of GGBS is approximately identical to that of cement. Geopolymer concrete was invented by Prof. Davidovits of France in the mid-1970s. He used the notion of aluminosilicate gel binding action to create inorganic polymer of aluminosilicates by combining silica and alumina from specially treated clay (metakaolin). GPCs are inorganic polymer composites with excellent strength and resistance to chloride penetration, acid assault, and other factors. When

compared to typical concretes, they are made by alkali activating industrial aluminosilicate waste materials like FA and GGBS. They have a very low greenhouse footprint. Geopolymers, unlike typical Portland/pozzolanic cements, do not use calcium-silicate-hydrates (CSHs) for matrix formation and strength, instead relying on the polycondensation of silica and alumina precursors. Source materials and alkaline liquids are the two major components of geopolymers. The raw materials should be silicon (Si) and aluminium (Al) rich aluminosilicates (Al). Fly ash, silica fume, slag, rice-husk ash, red mud, and other by-product products are examples. Because GPCCs are a novel class of materials, unlike traditional cement concretes, traditional mix design techniques are not typically relevant. The creation of GPCC mixes necessitates a comprehensive review of the components available.

2 Geopolymer synthesis

The source material must be rich in Silicon (Si) and Aluminum (Al), and an alkali activator such as sodium/potassium hydroxide is required for geopolymer production. In comparison to potassium hydroxide (KOH) with the addition of silicate solution to increase the dissolving process, sodium hydroxide (NaOH) is frequently utilised for geopolymer synthesis. The study indicates that geopolymers containing potassium activators have a reduced liquid requirement. The findings

* Corresponding author: ketananutakki@gmail.com

of the tests demonstrate that potassium activators improve component reactivity and hence compressive strength. Although sodium silicate and potassium silicate serve comparable functions as alkali activators, the K_2SiO_3/KOH components must be prepared differently from $Na_2SiO_3/NaOH$. The use of sodium silicate, on the other hand, has been proven to be more successful because sodium hydroxide solution promotes greater silicate and aluminate monomer breakdown from Fly ash. In comparison to KOH , geopolymer samples containing sodium hydroxide ($NaOH$) have a greater compressive strength. $NaOH$ has the maximum compressive strength of 47.92 MPa, whereas KOH has a compressive strength of 29.65 MPa. Because Na^+ has a lower ionic size than K^+ , it is more active and facilitates the dissolving of Si^{4+} and Al^{3+} ions from fly ash. Sodium silicate solution has a higher viscosity than potassium silicate solution, which allows it to use less liquid phase, resulting in lower porosity, shrinkage, compressive strength, and durability. In this study, two types of fly ashes were utilised to create geopolymer concrete: C class (high calcium content) and F class (low calcium content) as per ASTM C618, in order to analyse the influence of high and low CaO content fly ashes on the polymerization process. In low calcium fly ash based geopolymer concrete mixes, sodium aluminosilicate hydrate (N-A-S-H) gel is the main reaction product, whereas calcium silicate hydrate (C-S-H) and calcium aluminosilicate hydrate (C-A-S-H) gels coexisted with sodium aluminosilicate hydrate (N-A-S-H) gel as the main reaction products in high calcium fly ash. When cured at room temperature, the high CaO concentration improves the strength development.

3 Formulating the GPCC mixes

The compressive strength increased with increase in percentage of GGBS and also with an increase in AAS/ ratio. Thus, we can say that there is consistent increase in strength for an increase in AAS/ ratio from 0.40 to 0.50 but the strength has greatly reduced when the AAS/ ratio is further decreased, which shows the scarcity of fluid cannot impart strength due to weak activation. The mix ingredients of geopolymer concrete are

1. 16M $NaOH/KOH$
2. $SiO_2/Na_2O = 2.0$ or $SiO_2/K_2O = 2.0$
3. $Na_2SiO_3/NaOH = 2.5$ or $K_2SiO_3/KOH = 2.5$
4. Fly Ash = 450 kg/m^3
5. Alkali Activator solution (AAS) / Fly ash = 0.40
6. Fine aggregate = 505 kg/m^3
7. 20mm Coarse aggregate = 1246 kg/m^3
8. 60°C temperature oven heat cured for 24h period
9. Rest period = 0 days (casted cubes are immediately sealed and kept in oven with moulds on)

Mix design is developed as per IS:10262 procedure and the powdery content of Portland cement is replaced by equivalent solid volume of Geopolymeric Source Material (FA) and liquid portion of water by Activator Solution on equal volume basis in Geopolymer Concrete while Aggregate content remains same in both the concretes.

It is noted here the liquid component of GPCs is not readily available in the market, unlike water in case of conventional concrete. It is also worth noting there that the effective specific chemical additives such as retarders, accelerators, etc (which are very common for Portland cements) are not yet specifically developed for geopolymers. Therefore, field adjustments would not be easy always.

Because GPCs are a novel class of building materials, there are no standard mix design methods for them, unlike ordinary cement concrete. As a result, the proportioning of GPC was done by trial and error, with strength and workability qualities in mind. There was no more water added. When compared to a 0 day rest time, it was shown that a 1 day rest period offers a greater compressive strength.

6 Effect of different types of Alkaline activator solutions

In this study two types of alkaline activator solutions such as $Na_2SiO_3/NaOH$ and K_2SiO_3/KOH are used to study their effect on the compressive strength of geopolymer concrete (GPC).

Table 1. Compressive strength of GPC made with various alkaline activator solutions

Type	Compressive Strength (MPa)
GPC made with $Na_2SiO_3/NaOH$	47.92
GPC made with K_2SiO_3/KOH	29.65

Fig. 1. Compressive strength of GPC made with various alkaline activator solutions

Literature shows that K₂SiO₃/KOH yields better performance than Na₂SiO₃/NaOH and also K₂SiO₃/KOH alkali activator solution is expensive. But in our study the it was observed that the K₂SiO₃/KOH performance was inferior to Na₂SiO₃/NaOH, which proves that adopted alkali concentration (16M), oxides ratio (2.0) and activator/alkali ratio (2.5) may yield superior performance

for Na₂SiO₃/NaOH but did not work for K₂SiO₃/KOH. So, after much trials, the optimum ratio values are obtained using which GPC mixes made with K₂SiO₃/KOH are developed.

Due to the high calcium concentration available in Class C raw fly ash material, GPC manufactured with Class C fly ash has a greater compressive strength at ambient temperature than GPC created with Class F fly ash. Because GPC produced with Class F fly ash fails to attain structural integrity at room temperature, it is treated to 60°C heat curing. At high temperatures, GPC produced with Class F fly ash outperforms GPC created with Class C fly ash in terms of strength.

It was found that the increase in molarity decreases workability of geopolymer concrete. Also, the workability increases with increase in fly ash (FA) content and AAS/FA ratio in geopolymer concrete. Past literature reports that the improved workability was noticed when M-sand was used in geopolymer concrete.

Workability decreases with decrease of AAS/FA ratio but compressive strength increases. Compressive and split tensile strengths decrease with increase in fly ash content.

Table 2. Compressive strengths of GPC made with different types of fly ashes

Type	Initial Setting time (minutes)	Compressive Strength (MPa)	Curing Type
GPC made with Class C fly ash (>20% CaO as per ASTM)	254	37.22	Ambient curing for 28 days
	254	55.34	Heat curing at 60°C temperature; Rest period=1 day
GPC made with Class F fly ash (<10% CaO as per ASTM)	2889	35.34	Ambient curing for 28 days
	Not applicable	47.92	Heat curing at 60°C temperature; Rest period=0 day

Table 3. Workability of GPC mixes made with various molarities of NaOH

AAS/FA=0.50 Na ₂ SiO ₃ /NaOH=2.5 SiO ₂ /Na ₂ O=2.0 Fly Ash = 450 kg/m ³ Fine aggregate=505 kg/m ³ 20mm Coarse aggregate= 1246 kg/m ³	NaOH Molarity	Slump (mm)
	8M	205 (Shear slump)
	10M	163
	12M	144
	14M	128
	16M	109
	18M	54

Table 4. Workability of GPC mixes made with different fly ash content

AAS/FA=0.50 Na ₂ SiO ₃ /NaOH=2.5 SiO ₂ /Na ₂ O=2.0 NaOH Molarity= 16M Fine aggregate=505 kg/m ³ 20mm Coarse aggregate= 1246 kg/m ³ Density of Concrete=2426 kg/m ³	Fly Ash(kg/m ³)	Slump (mm)
	300	50
	350	67
	400	89
	450	109
	500	129
	550	166

Table 5. Workability of GPC mixes made with different AAS/FA ratio

Na ₂ SiO ₃ /NaOH=2.5	AAS/FA ratio	Slump (mm)
--	--------------	------------

$\text{SiO}_2/\text{Na}_2\text{O}=2.0$ NaOH Molarity= 16M $\text{Fly Ash} = 450 \text{ kg/m}^3$ $\text{Fine aggregate}=505 \text{ kg/m}^3$ $20\text{mm Coarse aggregate}= 1246 \text{ kg/m}^3$	0.40	88
	0.50	109
	0.60	137
	0.70	164
	0.80	202
	0.90	234(Collapse)

Table 6. Strengths of GPC mixes made with different fly ash content

$\text{AAS/FA}=0.50$ $\text{Na}_2\text{SiO}_3/\text{NaOH}=2.5$ $\text{SiO}_2/\text{Na}_2\text{O}=2.0$ NaOH Molarity= 16M	Fly Ash(kg/m^3)	Compressive Strength (MPa)	Split-tensile Strength (MPa)
	300	51.02	4.82
	350	49.13	4.44
	400	48.39	3.98
	450	47.92	3.67
	500	35.90	3.32
	550	31.25	2.86

7 Conclusions

1. If formulated meticulously GPC made with $\text{K}_2\text{SiO}_3/\text{KOH}$ yields better performance than GPC made with $\text{Na}_2\text{SiO}_3/\text{NaOH}$. Otherwise both alkaline activator solutions are achieving the intended strengths at their respect
2. Due to the high calcium concentration available in Class C raw fly ash material, GPC manufactured with Class C fly ash has a greater compressive strength at ambient temperature than GPC created with Class F fly ash. Because GPC produced with Class F fly ash fails to attain structural integrity at room temperature, it is treated to 60°C heat curing. At high temperatures, GPC produced with Class F fly ash outperforms GPC created with Class C fly ash in terms of strength.
3. It was found that the increase in molarity decreases workability of geopolymer concrete. Also, the workability increases with increase in fly ash (FA) content and AAS/FA ratio in geopolymer concrete.
4. It was found that the increase in molarity decreases workability of geopolymer concrete. Also, the workability increases with increase in fly ash (FA) content and AAS/FA ratio in geopolymer concrete.
5. Compressive and split tensile strengths decrease with increase in fly ash content.

References

1. Srinivas. T, Abhignya. G and Ramana Rao. N.V, A Review on Geopolymer RCC Beams made with Recycled Coarse Aggregate, E3S Web of Conferences, ICMED, 10-12 July 2020, India (2020).
2. M. Kavitha, P. B. Bobba and D. Prasad, *2016 7th India International Conference on Power Electronics (IICPE)*, 2016, pp. 1-6
3. T. Srinivas, S. V. Srinidhi and N.V. Ramana Rao, A Review on Flexural Behavior of RCC Beams Made with Geopolymer Concrete, E3S Web of Conferences, ICMED, 10-12 July 2020, India (2020).
4. T. Srinivas, P. Bhavana, and N. V. Ramana Rao, Effect of Manufactured Sand on Flexural Behavior of Geopolymer RCC Beams: A review, E3S Web of Conferences, ICMED, 10-12 July 2020, India (2020).
5. T. Srinivas and N.V. Ramana Rao, IJCIET, Volume **10**, 510 (2019).
6. K. Sai Gopi, Dr. T. Srinivas and S. P. Raju V, E3S Web of Conferences ICMED 184, 01084GRIET, 28-29 February, [https://doi.org/10.1051/e3sconf/2020184011084\(2020\)](https://doi.org/10.1051/e3sconf/2020184011084(2020))
7. Jagannadha Kumar, M.V., Jagannadha Rao, K., Dean Kumar, B., Srinivasa Reddy, V., Int. J. of Civil Eng. and Tech., 9(7), pp. 1133-1141 (2018)
8. Ganta, J.K., Seshagiri Rao, M.V., Mousavi, S.S., Srinivasa Reddy, V., Bhojaraju, C., Structures 28, pp. 956-972 (2020)
9. S. Seshadri, M. Kavitha and P. B. Bobba, *2018 International Conference on Power, Instrumentation, Control and Computing (PICC)*, 2018, pp. 1-6
10. Naidu, K.S.S.T., Rao, M.V.S., Reddy, V.S., Int. J. of Innov. Tech. and Explor. Eng.g (IJITEE), 8(9 Special Issue 2), pp. 641-642 (2019)
11. Chandana Priya, C., Seshagiri Rao, M.V., Srinivasa Reddy, V., Int. J. of Civil Eng. and Tech., 9(11), pp. 2218-2225 (2018)
12. Satya Sai Trimurthy Naidu, K., Seshagiri Rao, M.V., Srinivasa Reddy, V., Int. J. of Civil Eng. and Tech., 9(11), pp. 2383-2393 (2018)
13. Supriya, Y., Srinivasa Reddy, V., Seshagiri Rao, M.V., Shrihari, S., Int. J. of Rec. Tech. and Engi., 8(3), pp. 5381-5385 (2019)
14. Kotkunde, N., Krishna, G., Shenoy, S.K., Gupta, A.K., Singh, S.K. International Journal of Material Forming, 10 (2), pp. 255-266 (2017)

15. Govardhan, D., Kumar, A.C.S., Murti, K.G.K., Madhusudhan Reddy, G. *Materials and Design*, 36, pp. 206-214. (2012)
16. A.U. Haq, A. K. Kavitha, T. Rao, T. Buddi, D. Balaji, K. Satyanarayana, S. K. Singh, *Materials Today: Proceedings*, **18**, 4589 (2019)
17. Kumar, P., Singhal, A., Mehta, S., Mittal, A. *Journal of Real-Time Image Processing*, 11 (1), pp. 93-109. (2016)
18. Srinivas Rao J, S K Tummala, Kuthuri N R, Indonesia Journal of Electrical Engg. & Computer Science, **21** (723), 2020
19. Raghunadha Reddy, T., Vishnu Vardhan, B., Vijayapal Reddy, P. *International Journal of Applied Engineering Research*, 11 (5), pp. 3092-3102 (2016)
20. Hussaini, S.M., Krishna, G., Gupta, A.K., Singh, S.K. *Journal of Manufacturing Processes*, 18, pp. 151-158 (2015)