

Progress in the application of Cu-based catalysts in the electroreduction of CO₂ to produce C_xs products

Lei Wang^{1,*}, Mengling Liu², Yichen Yu¹, Mingzhen Wei¹, Chunlei Li²

¹Department of Chemical Engineering and Technology, Lanzhou University of Technology, Qilihe District, Lanzhou, Gansu, China

²Department of Chemical Engineering, Lanzhou University of Technology, Qilihe District, Lanzhou, Gansu, China

Abstract: Since the industrial revolution, human dependence on fossil fuels has resulted in increasingly severe atmospheric carbon dioxide (CO₂) emissions. Electrocatalytic CO₂ RR has attracted much attention because of its many advantages, such as mild reaction conditions, controllable reaction rate, low cost and scalable electrolyzer.^[7] More importantly, electrocatalytic CO₂ RR can control the selective generation of target products by rationally adjusting the reaction potential, electrolyte and catalyst species. However, the CO₂ molecular structure is stable, and obtaining the key CO₂-based anionic intermediate CO₂⁻ from activated CO₂ molecules requires overcoming a huge energy barrier. Copper (Cu) catalysts are the only monometallic catalysts to date that can form two-carbon (C₂) products, which establishes their special position in the field. However, the poor selectivity of Cu for a particular product has led to a wide distribution of reduction products, covering the range from carbon monoxide (CO), a reduction product at 2e⁻, to ethanol (C₂H₅OH), a reduction product at 12e⁻. Meanwhile, Cu catalysts are generally less stable, which can seriously affect their commercialization. Currently, in order to obtain highly selective C₂+ products (mainly ethylene and ethanol),^[16] this article reviews the various methods developed by different scholars in China and abroad to modify Cu catalysts. Finally, this article suggests ways to improve the performance of Cu-based catalysts to enhance the Faraday efficiency of the C₂ product from the electroreduction of CO₂ and gives an outlook on the future direction of Cu-based catalysts.^[19]

1. Introduction

The carbon cycle of nature can no longer accommodate the excessive amount of CO₂, and the resulting ecological problems such as global warming have had a significant impact on the natural environment and human development. Reducing greenhouse gas emissions and lowering the level of CO₂ gases in the atmosphere has become a broad consensus of the international community. Utilizing solar energy or other forms of renewable energy to create an artificial carbon cycle by converting CO₂ into valuable chemicals is an effective strategy for eliminating excess CO₂. This not only alleviates the energy and environmental crises caused by excess carbon emissions, but also creates a carbon economy of great economic value. Currently, the utilization of CO₂ reduction reaction (CO₂ RR) based on biological, thermochemical, photochemical and electrochemical methods has been widely studied.

Compared with other methods, it is therefore very difficult to achieve the reduction of chemicals, even selective reduction, which is one of the major reasons why CO₂ RR has not been industrially applied so far. Therefore, there is an urgent need to prepare efficient and stable electrocatalysts to improve the selectivity,

conversion, economy and stability of CO₂ RR, including surface engineering, organic modification and addition of other elements to them.^[14] The combination of other metal elements with copper may modulate the product selectivity by modulating the affinity of the product for carbon and oxygen, thus affecting the intermediate adsorption. However, due to the complexity of the mechanistic pathways, how many metal elements to add is still largely a matter of trial-and-error screening, which is very time-consuming. For this reason the development of high performance electrocatalysts remains one of the research priorities in this field.

2. Status of research

This chapter gives the current status of domestic and international efforts for the electroreduction of CO₂ over copper-based catalysts.

2.1. Current status of foreign research

(Lin et. al., 2020) study operando time-resolved x-ray absorption spectroscopy reveals the chemical nature enabling highly selective CO₂ reduction. A systematic time-resolved study can provide key insights on selective carbon dioxide electro-reduction. (Wu et. al., 2020)

* Corresponding author: 1063456257@qq.com

report that a nanodendrite configuration for Cu catalyst can improve the electrocatalytic performance of Cu catalysts, especially multicarbon product formation, while suppressing HER and methane production. [8](Arán-Ais et. al., 2020) report improved efficiency towards ethanol by tuning the morphology and oxidation state of the copper catalysts through pulsed CO₂ electrolysis. [9](Li et. al., 2021) demonstrate a facile cation exchange method to synthesize Ag/Cu electrocatalysts for CO₂ reduction using Cu sulfides as a growth template. [11](Xiao et. al., 2021) summarize recent progress that has been achieved by tailoring the electrocatalyst architecture for efficient electrochemical CO₂ conversion to the target C₂ products. [12](Peng et. al., 2021) study double sulfur vacancies by lithium tuning enhance CO₂ electroreduction to n-propanol. The work suggests an attractive approach to create anion vacancy pairs as catalytic centers for multi-carbon-products. (Cao et. al., 2021) offer an effective avenue to design electrocatalysts for the highly selective CO₂RR to produce multicarbon products via a tandem route. Since the initial Cu²⁺ active sites are hard to retain, there have been few studies about Cu²⁺ catalysts for CRR. [13] (Zhou et. al., 2022) propose a solid-solution strategy to stabilize Cu²⁺ ions by incorporating them into a CeO₂ matrix, which works as a self-sacrificing ingredient to protect Cu²⁺ active species. [14]

2.2. Current status of domestic research

(Shengnan Wang et al.,2023)pointed out that the electrocatalytic reduction of CO₂ is expected to alleviate the problems of depletion of fossil fuels and increasing concentration of CO₂ in the atmosphere at the same time. However, there is still a great challenge to improve the selectivity of the high-value-added multicarbon products for electrocatalytic CO₂ reduction. Therefore, they designed an activation strategy for oxide-derived copper electrodes to construct the Cu₂O-Cu interface, and synergistically promoted the electrocatalytic CO₂ reduction with Cu⁺ and CuO to generate C₍₂₊₎ products with high efficiency and high selectivity. They demonstrated that the synergistic effect of Cu⁰ and Cu⁺ at the Cu₂O-Cu interface could indeed enhance the selectivity of specific high-value-added multicarbon products in the electrocatalytic reduction of CO₂. [2](Yongda et al., 2021, 22, 23). (Y.D. Zhang et al., 2021) showed that Cu-based nanocatalytic materials were prepared to facilitate the reduction of CO₂ to C₂ products at low overpotentials. The catalysts were prepared, characterized, structurally and compositionally analyzed and electrochemically tested. This stabilizes the generation of C₂ products as well as improves the

electrocatalytic activity of Cu-based catalysts. [5] (Niu Di et al., 2021) pointed out that the introduction of another metal to form a tandem catalyst on top of a Cu-based catalyst is an effective way to improve the selectivity of multicarbon products. The tandem catalyst can convert CO₂ to carbon monoxide (CO) over the introduced metal, which is subsequently reduced to the multicarbon product by the copper-based catalyst. Based on cuprous oxide (Cu₂O) catalysts, they introduced silver (Ag) and gold (Au) to form tandem catalysts with Cu₂O with the aim of achieving highly selective electrocatalytic reduction of CO₂ to C₂ products and providing a new idea for the macro preparation of nano-sized Cu₂O tandem catalysts. [6]

3. Commentary

The application of catalysts for the electroreduction of CO₂ to produce the C₂₊ product has been analyzed in detail by our scholars, and it has been found that most of the catalysts suffer from the problems of low selectivity for the C₂ product and weak catalytic activity. On the other hand, Cu is widely used as a CO₂ RR catalyst due to its moderate affinity for CO and can be used for subsequent C-C coupling, which can generate a large amount of C₂ product in aqueous solution with high efficiency and kinetic activity. [18]

Existing studies by our scholars show that the selectivity of Cu-based catalysts for highly reduced products is still low; on the other hand, Cu is the only active component reported so far that can be used for the production of highly reduced products, but it still suffers from the drawbacks of high overpotentials and low Faraday efficiencies (slow kinetics of the conversion of CO₂ to CO on Cu), which leads to the low efficiency of the CO₂ RR for the production of highly reduced products.

In this review, we summarize the recent strategies used by the scientific community (as shown in Table 1 below) including oxide and halide-derived copper nanoparticles. Specifically for the reduction of electrochemical CO₂ to polycarbon hydrocarbons and related oxygenated compounds. Obtaining C₂₊ products is a challenge because copper-based catalysts have different selectivities for different products. The researchers involved are trying to control the properties associated with copper-based catalysts to obtain the products we need.

Table 1 Kinetic activity, and is widely used as a CO₂RR catalyst.

Types	Catalyst	Electrolyte	Synthesis method	Performance parameters	Ref.
Oxide derived	cv treated copper electrode	0.1mol KHCO ₃	Cu electrodes were prepared by PVD, then treated with Cv and electrodeposited on silicon wafers, and the prepared Cu electrodes were	Main products electrodeposited copper H ₂ , methane, formic acid finite elements 50%, 30% and 10%	[14]

Halide derived	CuX (X = Cl, Br or I)	0.1 mol KHCO ₃	cycled and chemically deposited in the potential region of 0.55-0.3v, respectively.	Electropolished copper foil synthesized by electrophoresis in different 0.1 M potassium salt solutions	FE C ₂₊ : 80 % on cuprous iodide at 0.9 V, about 66-73 % on cuprous bromide and cuprous chloride at 1.0 V; partial geometric current density: about 31.2 mA cm ² on cuprous iodide electrode	[17]

To address such issues, this article reviews the modification strategies of Cu-based catalysts to improve the performance of the C₂₊ product from the electroreduction of CO₂.

(1) The multi-step PCET (proton-coupled electron transfer) treatment of sequential intermediates suggests that tuning the adsorption energy of specific reaction intermediates on the catalyst surface to the appropriate level is an effective means of facilitating the selectivity of the C₂ product. In addition, the ease of C-C coupling depends on the surface coverage and adsorption sites of CO. Based on the above theoretical principles, researchers have carried out extensive modification and design of Cu-based catalysts to tune the adsorption capacity of the key intermediates.^[1]

(2) Researchers can also construct environments with high CO concentrations, including designing unsaturated coordination atoms, controlling the oxidation state of Cu, preparing Cu nanocubes with different crystalline surfaces, and constructing tandem catalytic systems. The size, morphology and structure of the nanomaterials determine the average number of coordinating atoms in the catalyst.^[3]

(3) The coordination number and atomic environment affect the orbital overlap between the surrounding electrons, changing the electronic structure of the active component, which can directly affect the reactivity of the catalyst and substrate. Monoatomic copper has the smallest coordination number.^[4]

(4) Since the electronic structure of monoatomic Cu is fundamentally different from that of native Cu, this also leads to a general lack of C-C coupling ability of monoatomic Cu, whose electrolysis products are mainly C₁ products such as CH₃OH, CH₄, CO. In oxide studies, it has been found that the near-surface oxygen of oxidized derivatives of Cu can reduce the σ-repulsion between CO and surface Cu atoms by extracting the electron density from the surface atoms, thus increasing the bonding strength of CO. CO dimerization is a key step in the formation of the C-C bond and is accompanied by the Cu surface after In addition, oxidized derivatives of Cu can also induce positive interactions between Cu⁰ and Cu⁺ through the formation of a mixed-valence state, thereby significantly increasing the C-C coupling capacity of CuO. The positive interaction between CuO and Cu⁺ can be induced by the formation of

mixed valence states, which significantly improves the selectivity of the C product.^[10]

4. Summary and outlook

(1) In this article, we consider that the C-C coupling reaction, which determines the selectivity of single-carbon (C₁) or multicarbon (C₂₊) products, is a thermocatalytic step that does not involve the transfer of protons and electrons, and thus the catalyst material and surface structure play a decisive role in it. ^[15]Therefore, our next research direction utilizes nanotechnology principles to design fine and rational electrocatalyst structures that can significantly affect the adsorption energies of some key intermediates and thus the inherent reaction pathways of Cu catalysts;

(2) The combination of other metal elements with Cu may affect the intermediate adsorption by modulating the product selectivity through regulating the affinity of the product for carbon and oxygen. However, due to the complexity of the mechanistic pathway, the amount of metal elements to be added is still largely a matter of trial-and-error screening. Therefore, in order to develop high-performance Cu-based electrocatalysts, our next step could be to explore composite Cu-based catalysts with better performance for the electroreduction of CO₂ product C₂₊ product by comparing the activities of different metal additions into the Cu-based catalysts.^[20]

References

1. Zekun Zhang, Xiaosheng Jing, Hao Xu et al. Progress in the design and reaction mechanism of copper-based catalysts for electrocatalytic carbon dioxide reduction[J/OL]. Analytical Chemistry:1-20[2023-03-25].
2. Shengnan Wang, Dan Wang, Benqiang Tian et al. Synergistic promotion of electrocatalytic CO₂ reduction by Cu⁺ and CuO at the Cu₂O-Cu interface for efficient and highly selective generation of C₍₂₊₎ products (in English) [J]. Science China (Materials), 2023,66(05):1801-1809.
3. Huanhuan Yang,Shiying Li,Qun Xu. Regulatory strategies for the preparation of C₍₂₊₎ products by

- electrocatalytic reduction of CO₂ with high efficiency over copper-based catalysts (in English)[J].Chinese Journal of Catalysis,2023,48(05):32-65.
5. Y.D. Zhang. Preparation of nano-copper-based catalysts and their electrocatalytic CO₂RR to C₂ products [D]. China University of Petroleum (Beijing), 2021.DOI:10.27643/d.cnki.gsybu.2021.001320.
6. Niu Di. Study on electrocatalytic reduction of CO₂ to C₂ products over Ag and Au doped Cu₂O catalysts [D]. University of Science and Technology of China, 2021.DOI:10.27517/d.cnki.gzkju.2021.001050
7. Meng Li, Yue Hu, Tianci Wu, Afriyanti Sumboja, Dongsheng Geng,How to enhance the C₂ products selectivity of copper-based catalysts towards electro-chemical CO₂ reduction?-A review, Materials Today, 2023, ISSN 1369-7021,.
8. Minfang Wu; Chang Zhu; Kang Wang; Guihua Li; Xiao Dong; Yanfang Song; Jiamin Xue; Wei Chen; Wei Wei; Yuhua Sun; "Promotion of CO₂ Electrochemical Reduction Via Cu Nanodendrites", ACS APPLIED MATERIALS & INTERFACES, 2020. (IF: 3)
9. Rosa M. Arán-Ais; Fabian Scholten; Sebastian Kunze; Rubén Rizo; Beatriz Roldan Cuenya; "The Role of in Situ Generated Morphological Motifs and Cu(i) Species in C₂+ Product Selectivity During CO₂ Pulsed Electroreduction", NATURE ENERGY, 2020. (IF: 5)
10. Gracita M Tomboc; Songa Choi; Taehyun Kwon; Yun Jeong Hwang; Kwangyeol Lee; "Potential Link Between Cu Surface and Selective CO₂ Electroreduction: Perspective on Future Electrocatalyst Designs", ADVANCED MATERIALS, 2020. (IF: 3)
11. Jinghan Li; Junrui Li; Chaochao Dun; Di Zhang; Jiajun Gu; Jeffrey J. Urban; Joel Ager; "Copper Sulfide As The Cation Exchange Template for Synthesis of Bimetallic Catalysts for CO₂ Electroreduction", 2021.
12. Changlong Xiao; Jie Zhang; "Architectural Design for Enhanced C₂ Product Selectivity in Electrochemical CO₂ Reduction Using Cu-Based Catalysts: A Review", ACS NANO, 2021. (IF: 3)
13. Rong Cao; Dong-Li Meng; Meng-Di Zhang; Duan-Hui Si; Min-Jie Mao; Ying Hou; Yuan-Biao Huang; "Highly Selective Tandem Electroreduction of CO₂ to Ethylene Over Atomically Isolated Nickel-Nitrogen Site/Copper Nanoparticle Catalysts", ANGEWANDTE CHEMIE, 2021. (IF: 3)
14. Xianlong Zhou; Jieqiong Shan; Ling Chen; B. Xia; T. Ling; Jingjing Duan; Y. Jiao; Yao Zheng; S. Qiao; "Stabilizing Cu²⁺ Ions By Solid Solutions to Promote CO₂ Electroreduction to Methane", JOURNAL OF THE AMERICAN CHEMICAL SOCIETY, 2022. (IF: 3)
15. T.-C. Chou, C.-C. Chang, H.-L. Yu, W.-Y. Yu, C.-L. Dong, J.-J. Velasco-Vélez, C.-H. Chuang, L.-C. Chen, J.-F. Lee, J.-M. Chen, Controlling the oxidation state of the Cu electrode and reaction intermediates for electrochemical CO₂ reduction to ethylene, J. Am. Chem. Soc. 142 (2020) 2857–2867.
16. W. Zhang, C. Huang, Q. Xiao, L. Yu, L. Shuai, P. An, J. Zhang, M. Qiu, Z. Ren, Y. Yu, Atypical oxygen-bearing copper boosts ethylene selectivity toward electrocatalytic CO₂ reduction, J. Am. Chem. Soc. 142 (2020) 11417–11427.
17. B. Zhang, J. Zhang, M. Hua, Q. Wan, Z. Su, X. Tan, L. Liu, F. Zhang, G. Chen, D. Tan, Highly electrocatalytic ethylene production from CO₂ on nanodefected Cu nanosheets, J. Am. Chem. Soc. 142 (2020) 13606–13613.
19. D. Gao, I. Sinev, F. Scholten, R.M. Arán-Ais, N.J. Divins, K. Kvashnina, J. Timoshenko, B. Roldan Cuenya, Selective CO₂ electroreduction to ethylene and multicarbon alcohols via electrolyte-driven nanostructuring, Angew. Chem. Int. Ed. 58 (2019) 17047–17053.
20. M.G. Kibria, C.T. Dinh, A. Seifitokaldani, P. De Luna, T. Burdyny, R. Quintero-Bermudez, M.B. Ross, O.S. Bushuyev, F.P. García de Arquer, P. Yang, Asurface reconstruction route to high productivity and selectivity in CO₂ electroreduction toward C₂+ hydrocarbons, Adv. Mater. 30 (2018) 1804867.